C² STAIN SAFE™

Step-by-Step Application Instructions – C² Stain Safe

Before beginning, always read SDS and technical data sheet for complete instructions and safety information. Always prepare a test panel before proceeding.

C² STAIN SAFE™ (ON BROOMED, STEEL TROWELED AND GROUND/POLISHED FLOORS)

- It is important to apply this product per appropriate coverage rates to insure maximum chemical resistance. If you put it on to thin it will not work as well. Application temperature should be in 4°C - 38°C range.
- C² Stain Safe™ is a breathable product, allowing the concretes natural moisture to dissipate slab. Thus will never peel or crack. Because of this, C² Stain Safe™ will allow you a window of time to clean up petroleum base spills. 6-8 hours. Over time petroleum base spills will penetrate. Clean protected floors with C² Maintenance™ and auto-scrubber.

SEMI-POROUS SURFACE

- 3.75-7.50 m2/liter

NON-POROUS SURFACE

- 7.50-15.00 m2/liter
- Ensure concrete is clean and free of dust and debris.
- Use low-pressure pump sprayer with fan tip for C² Stain Safe™ applications. Do not dilute.
- Make sure the entire surface is wet by dense mist. On porous concrete a 2nd application may be necessary to ensure proper stain resistance. 2nd coat must be applied while 1st coat is still damp, due to its ability to repel itself once 1st coat dries.
- Do not over apply or puddle on the surface. Microfiber mop in areas that may puddle.
- Protect treated surfaces from traffic for 4 hours after application.
- Avoid liquids for 24 hours.
- C² Stain Safe™ will be fully cured and have maximum chemical resistance after 3 days cure.